



Clay | Glazes | Art Supplies | Pottery | Ceramics

www.sarashop.in

HOW TO MIX GLAZE

Materials Required:

1. A bucket or container to mix the glaze
2. Sieve - 80 mesh
3. 600ml clean water (approx.) **This is for 1kg powdered glaze.**
4. Mixing Spatulla
5. Balloon Whisker (optional)
6. Weighing scale to measure
7. Hand gloves and face mask

STEPS:

1. Pour 250 ml water in the bucket.
2. Unpack and open Sara Glaze container.
3. Start mixing small portions of the glaze powder into the water, keep stirring as you add, to avoid lumps. Add more water as you increase the amount of glaze powder. Do not exceed 600ml of water.
4. Keep stirring and mixing well, make sure no lumps are present.
5. Sieve this mixture through the 80 mesh.
6. Allow a settling time of minimum 6 hours before using it.
7. Store the liquid glaze in a closed air tight container.

TESTING:

1. Testing the glaze is highly recommended. Try it on a test piece before applying it on the finished piece.
2. The liquid consistency and thickness can be variable. After testing the glaze, if required, add or reduce water. Inorder to reduce the water, allow the glaze to settle in the container for a few days, water collects at the top, this can be taken out using a cup or syringe. Test again and use.

APPLICATION METHODS:

1. Dipping, Pouring, brushing and Spraying. Minor variations will arise due to application methods, test and choose the best method suitable for your product.

Pls Note:

Sara glazes are tested in the oxidation kiln. Colours and results shown in the product images are a result of oxidation firing.

For doubts and enquiries, write to us at sara.artproducts@gmail.com